

MATERIAL DATA SHEET · DUPLEX STAINLESS STEEL

ASTM A790 UNS S31803 — Chemical Composition & Mechanical Properties

Teshi Group document TG-MG-073 · Rev. 1 · October 2026 · www.teshigroup.com/material-grades/astm-a790-s31803/

ASTM A790 UNS S31803 is a duplex stainless steel grade for seamless & welded pipe (UNS S31803, EN / W.Nr 1.4462). It is also known as 2205 / UNS S31803. This sheet summarises its chemical composition limits, minimum mechanical properties, heat treatment and typical service. Teshi Group supplies this grade as a stockist and supplier, and manufactures matching flanges and fittings.

At a glance

Material family	Duplex stainless steel
Product form	Seamless & welded pipe
UNS	S31803
EN / W.Nr	1.4462
Also known as	2205 / UNS S31803
PREN (min values)	30.5

Mechanical properties

Tensile strength, min	620 MPa
Yield strength (0.2 % offset), min	450 MPa
Elongation, min	25 %
Hardness	290 HBW max

Chemical composition (weight %)

C 0.030 max	Mn 2.00 max	P 0.030 max	S 0.020 max	Si 1.00 max
Cr 21.0–23.0	Ni 4.5–6.5	Mo 2.5–3.5	N 0.08–0.20	

Single values are maximums unless shown as a range or “min”.

Heat treatment

Solution annealed 1020–1100 °C, rapid cool

Typical service

Duplex pipe for chloride service and produced water

International equivalents (nearest)

USA — ASTM / ASME	ASTM A790 UNS S31803 · ASME SA-790 UNS S31803
USA — UNS	S31803
Europe — EN designation	X2CrNiMoN22-5-3
Europe — W.Nr	1.4462
Japan — JIS	SUS329J3L
China — GB / NB	S22253 / S22053 (022Cr22Ni5Mo3N / 022Cr23Ni5Mo3N)
China — old GB designation	00Cr22Ni5Mo3N
UK — BS (withdrawn)	318S13

Teshi Group — OEM manufacturer of flanges, pipe fittings, fasteners, valves and fabrications; stockist and supplier of pipes, plates and structural steel. ISO 9001:2015 · IBR approved · since 1971. Enquiries: info@teshigroup.com · sales@teshigroup.com · +91 78900 09110

Reference information compiled from the published standard for convenience. It does not replace the current edition of the governing standard, which takes precedence. Verify critical properties before design, purchase or fabrication. Teshi Engineers & Sales Promoters (P) Ltd accepts no liability for errors or omissions.